



up to
400 mm / 15.8"
thickness

The high-strength alloy: HOKOTOL

Characteristics

- low weight (approx. three times lighter in comparison to steel)
- excellent machinability (approx. five times better in comparison to steel)
- extreme uniform mechanical properties across the total thickness
- excellent mechanical properties in the centre of the plate
- excellent dimensional stability by stress relieved stretching or cold compressing
- excellent thermal conductivity (approx. four times higher in comparison to steel)
- excellent electrical conductivity (approx. two times higher in comparison to steel)

Fields of application

- moulds for blow forming and injection moulding for the plastic processing industry
- bolsters and force plates (punching technique)
- machine parts for high strength requirements at a low weight
- mechanical components with elevated mechanical properties

Characteristics of GIANTAL, WELDURAL and HOKOTOL

	Machinability	Uniformity	Dimension stability	Resistance to wear	Weldability	Polishability	Corrosion resistance
GIANTAL							
WELDURAL							
HOKOTOL							

not suitable very good suitable

Chemical composition

	Chemical elements	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Zr	Other Individual	Other Total
HOKOTOL	Min. weight (%)	0.00	0.00	1.5	0.00	1.8	0.00	5.7	0.00	0.08	0.00	0.00
	Max. weight (%)	0.30	0.35	2.6	0.1	2.6	0.05	7.6	0.06	0.25	0.05	0.15



up to
400 mm / 15.8"
thickness

Physical properties in comparison to steel

Property	Hardness	Density		E-Modulus		Coeff. of thermal expansion 20-100°C (68-212°F) 10 ⁻⁶ · K ⁻¹	Thermal conductivity at room temperature		Electrical conductivity at room temperature	
	HB	g/cm ³	lbs/ins ³	MPa	ksi		W/(m · K)	BTU · ins/ft ² · h · °F	m/Ω · mm ²	%IACS
HOKOTOL	180	2.83	0.10	70,300	10,200	23.5	154	1,067.8	23.0	39.7
Steel 1.2312 (40CrMnMoS86)	300	7.85	0.28	215,000	31,200	12.5	35	242.7	10.3	17.8
Relation Al : St	1 : 1.7	1 : 2.8	1 : 2.8	1 : 3.1	1 : 3.1	1.9 : 1	4.4 : 1	4.4 : 1	2.2 : 1	2.2 : 1

*IACS = Int. Annealed Copper Standard; BTU = British Thermal Unit

Guaranteed minimum values for various thicknesses

Thickness mm ins	Tensile strength R _m		Yield strength R _{p0.2}		Elongation (2") A ₅₀ %	
	MPa	ksi	MPa	ksi		
100	3.9	550	80.0	495	72.0	4.0
200	7.9	500	72.7	430	62.5	1.0
300	11.8	460	66.9	400	58.2	1.0
325	12.8	450	65.5	390	56.7	1.0

*at room temperature; measured at S/4; test direction L-T

Typical tensile properties for various thicknesses

Thickness mm ins	Tensile strength R _m		Yield strength R _{p0.2}		Elongation (2") A ₅₀ %	
	MPa	ksi	MPa	ksi		
100	3.9	575	83.4	535	77.6	7.5
200	7.9	545	79.0	485	70.3	4.0
300	11.8	515	74.7	455	66.0	2.0
400	15.7	485	70.3	415	60.2	2.0

*at room temperature; measured at S/4; test direction L-T

**Comparison of various mould alloys
dependent on the used type of plastic and the typical number of closures**

Type of plastic	Typical number of closures				
	< 1,000	< 50,000	< 150,000	< 500,000	< 2,000,000
Common plastics PP - PE - PET - PS - ABS	■ GIANTAL	■ WELDURAL	■ WELDURAL	■ WELDURAL (if mirror finished)	■ WELDURAL (if mirror finished)
PPO - PMMA - PC - PA - POM	■ GIANTAL	■ WELDURAL	■ WELDURAL	■ HOKOTOL	■ Steel
Talc charged plastics	■ WELDURAL	■ WELDURAL	■ WELDURAL	■ HOKOTOL (if surface coated)	■ Steel
GF charged plastics	■ WELDURAL	■ WELDURAL	■ HOKOTOL (if surface coated)	■ Steel	■ Steel
Elastomers NR - EPDM - NDR	■ WELDURAL	■ WELDURAL	■ WELDURAL	■ Steel	■ Steel

■ GIANTAL ■ WELDURAL ■ HOKOTOL ■ Steel

**Aleris Rolled & Extruded
Products - Europe**
„Marketing Communication“
56070 Koblenz · Germany

Contact in Germany
Carl-Spaeter-Straße 10

T +49 (0) 261 891 7329
F +49 (0) 261 891 9 7329
doreen.colausich@aleric.com
www.aleric.com

Contact in Belgium
A. Stocletlaan 87
2570 Duffel · Belgium

T +32 (0) 15 30 27 24
F +32 (0) 15 30 20 21
ann.van.dessel@aleric.com
www.aleric.com